

## HIGHTEC GREASEGUARD MoS2

Universal lithium mineral oil-based soap lubricating grease with molybdenum disulphide as a solid lubricant as well as corrosion and oxidation inhibitors. Recommended for use in sliding and rolling bearings that are subjected to high intermittent loads within a temperature range of -30°C to +130°C.

### Description

HIGHTEC GREASEGUARD MoS2 possesses outstanding walk stability, good cold flow ability and outstanding wear protection by using molybdenum disulphide i.a. as solid lubricant components.

HIGHTEC GREASEGUARD MoS2 also reliably protects against wear, even under extreme loads in mixed friction conditions.

### Application

The selected base oils and a premium lithium soap of the highest quality guarantee a walk-stable lubricating grease, even in the case of longer lubricating intervals, accompanied by a high mechanical load capacity.

Recommended for use in sliding and rolling bearings subjected to high loads at operating temperatures between -30°C and +130°C, for example in agriculture, in heavy-goods vehicles etc. or in other sectors in which high and/or oscillating forces are at work.

### The quality of this product is equivalent to EU regulations

- DIN 51 502/51 825: KPF 2 K-30
- T[°C]: -30 ... +130
- T[°F]: -22 ... +266

### Benefits

- Very good wear protection properties
- Very walk stable
- Outstanding resistance to oxidation
- Excellent pressure absorption capacity
- Good corrosion protection
- Very good resistance to water
- Good adhesive power

### Notices

If stored appropriately in originally sealed containers in a dry place, away from direct sunlight and at temperatures between 10°C and 30°C, the minimum storage period is 24 months.

A safety data sheet is available upon request for information on health, safety and environmental aspects. A little oil separation is caused by the product's attributes and harmless.

It is desirable to a certain extent to ensure lubrication, and no indication of inferior product quality. The separated oil can be incorporated again homogeneously by folding it in comprehensively.

### Typical characteristics

Property	Method	Unit	Value
Classification	DIN 51 502	-	KPF 2 K-30
	ISO 6743-9	-	ISO-L-X-CCEB2
NLGI-class	DIN 51 818	-	2
Thickener type	-	-	Lithium
Color	visuell	-	anthrazit / anthracite
Base oil viscosity at 40 ° C	ASTM D-7042	mm²/s	125
Worked penetration	DIN ISO 2137	0,1 mm	265 - 295
Dropping point	DIN ISO 2176	°C	> 185
VKA welding force	DIN 51 350-4	N	4000
Corrosion protection (Emcor)	DIN 51 802	Korr.-Grad	0-0
Corrosion effect on copper	DIN 51 811	Korr.-Grad	1 - 100
Resistance to water	DIN 51 807-1	Bew.-Stufe	1 - 90
Usage temperature	-	°C	-30 bis +130
Usage temperature	-	°F	-22 bis +266
Base oil	-	-	Mineralisch / mineral based

The characteristics shown are typical of current production. This data cannot be constructed as a legally binding warranty or guaranty of certain product properties or of the suitability of the product for a specific application. ROWE products are continually improved. Therefore ROWE reserves the right to change all the technical data in this product information at any time without notice. All sales and deliveries shall be subject to our current General Terms and Conditions of Sale and Terms ([www.rowe-oil.com](http://www.rowe-oil.com)).

ROWE MINERALÖLWERK GMBH  
Langgewann 101, D-67547 Worms



Are you looking for the correct oil for your vehicle?  
Scan this code for the ROWE-oilfinder.